



ACERO D2



SOLICITA



Composición química

%C	%Si	%Mn	%Cr	%Mo	%V
1.40 - 1.60	0.10 - 0.45	0.60 máx.	11.0 - 13.0	0.70 - 1.20	0.30 - 0.50

Propiedades Físicas

Dureza HB	Resistencia a la tensión	Elongación	Reducción de área
255 - 325	750 MPa	5 - 15%	20 - 30%